

QRFL0006 QUALIFICATION REPORT

M29F400B, M29W400B T6X-U35:

4 Mbit (x8/x16) Single Supply Flash Memory

INTRODUCTION

The M29F400B and M29W400B are 4 Mbit Single Supply (respectively 5V and 3V) Flash memory products with Boot Block partitioning and organized as 512 KByte of 8 bits each or 256 Kword of 16 bits each. Products can be programmed and erased in-system or in standard EPROM programmers.

The M29F400B and M29W400B are manufactured with the STMicroelectronics advanced CMOS 0.35 micron T6X-U35 process, especially developed for Flash memory products. The memory features a fast access time, low power consumption in all operations (Standby, Read, Erase and Program) and an endurance of 100,000 Program/Erase cycles per block.

Qualification Report History

- October 1999: Catania M5 Diffusion Line, TSOP48 (12 x 20mm) package
- October 1999: Catania M5 Diffusion Line, SO44 package

ST recognises that the quality of a product must be built-in during the design, material procurement, manufacturing and testing. Also that the reliability must be demonstrated before the product is released to full mass production. The qualification of new products and the certification of new processes is a rigorous task undertaken by Quality and Reliability professionals, to ensure stable products and processes capable of fully meeting customer requirements.

A key step of this activity is the Design Review where we assure that,

- adequate and realistic product specifications have been developed;
- design and layout rules, as documented in the Design Rules Manual, have been respected;
- critical performance parameters and process variables have been identified;
- previously untested design techniques or manufacturing processes are recognised;
- manufacturability concerns are identified;
- comprehensive and efficient qualification programs are defined.

Product Qualification is made on all new products and on new packages. Qualification is also remade on existing products when there are major changes to the design or manufacturing. The tests performed are tailored to the parameters affected by the major change or the combinations of new die or new package to be evaluated.

The results of the tests for this Flash memory are on the attached pages of this qualification report.

Director of Memory Products Group Quality Control & Reliability

Attilio PANCHIERI

Table 1. Revision History

Date	Revision Details
November 1999	First Issue
06/16/00	TSOP package related tests conditions change to be compliant to JEDEC 020A SO package related tests conditions change to be compliant to JEDEC 020A

Sub- group	Test Procedure	MIL-STD-883	Test Conditions	Result			Note
	Test Procedure	Procedure		Lots	Samp.	Fail	Note
1	Physical Dimensions	2016	Published Data				2
	Coplanarity TSOP48 Package		Published Data				2
2	Bond Strength	2011		1	30	0	
3	Die Attach Strength	2019 or 2027		1	10	0	
4	Radiography	2012		1	45	0	
5	Internal Visual and Mechanical	2014		1	5	0	
6	Solderability TSOP48 Package	2003	215°C, 3 sec, Precondition, 8 hrs, Steam aging	1	20	0	
7	Resistance to Solvents	2015	4 Solvent Solutions				2
8	Solder Coating Thickness and Compositions	(Note 1)	5 μm min Sn/Pb 85/15	1	20	0	
9	Resistance to Surface Mounting TSOP48 Package	JEDEC 020A	MSL 3	1	15	0	

 Note:
 1. According to ST specification.

 2. Results for similarity, from standard production monitor.

Sub- group	Test Procedure	MIL-STD-883 Procedure	Test Conditions	Results			Note
				Lots	Samp.	Fail	NOTE
1	Operating Life Test	1005	140°C, V _{CC} = 6V, – 168 hrs – 500 hrs	1	76 76	0 0	2,3
			140°C, V _{CC} = 4V, – 168 hrs – 500 hrs – 1000 hrs	1	76 76 76	0 0 0	2,4
2	Operating Life Test	1005	-40°C, V _{CC} = 6V, - 168 hrs - 500 hrs	1	32 32	0 0	2,3
			-40°C, V _{CC} = 4V, - 168 hrs - 500 hrs	2	64 64	0 0	2,4
3	Retention Bake	1005	250°C – 168 hrs – 500 hrs – 1000 hrs	1	60 60 60	0 0 0	2,3
4	Write/Erase Cycling		10,000 cycles 50,000 cycles 100,000 cycles	1	60 60 60	0 0 0	2,3
			10,000 cycles 50,000 cycles 100,000 cycles	1	63 63 63	0 0 0	2,4
5	Temperature, Humidity, Bias	CECC 90,000	85°C, RH = 85%, V _{CC} = 5.5V, – 168 hrs – 500 hrs	1	60 60	0 0	1,3
6	Temperature Cycling	1010C	−65 to 150°C, − 500 cycles − 1000 cycles	1	60 60	0 0	1,3
7	Pressure Pot		121°C, 2 Atm, RH = 100%, – 96 hrs – 168 hrs – 240 hrs	2	110 110 110	0 0 0	1,3

Table 3. TSOP48 (12 x 20mm) Plastic Package - Die Related Tests, Catania M5 Diffusion Line

Note: 1. Samples previously submitted to preconditioning flow for Surface Mounting devices according to the Package Related tests (previous page).

57

Test performed on CDIP48 package.
 Test performed on M29F400B device.

4. Test performed on M29W400B device.

4/7

Sub- group	Test Procedure	MIL-STD-883	Test Conditions	Result			Note
	Test Procedure	Procedure		Lots	Samp.	Fail	Note
1	Physical Dimensions	2016	Published Data				2
	Coplanarity SO44 Package		Published Data				2
2	Bond Strength	2011					2
3	Die Attach Strength	2019 or 2027					2
4	Radiography	2012		1	45	0	
5	Internal Visual and Mechanical	2014		1	5	0	
6	Solderability SO44 Package	2003	215°C, 3 sec, Precondition, 8 hrs, Steam aging				2
7	Resistance to Solvents	2015	4 Solvent Solutions				2
8	Solder Coating Thickness and Compositions	(Note 1)	5 μm min Sn/Pb 85/15				2
9	Resistance to Surface Mounting SO44 Package	JEDEC 020A	MSL 3	1	15	0	

 Note:
 1. According to ST specification.

 2. Results for similarity, from standard production monitor.

Sub-	Test Procedure	MIL-STD-883 Procedure	Test Conditions	Results			Note
group				Lots	Samp.	Fail	Note
1	Operating Life Test	1005	140°C, V _{CC} = 6V, - 168 hrs - 500 hrs	1	70 70	0 0	2,3
			140°C, V _{CC} = 4V, - 168 hrs - 500 hrs	1	48 48	0 0	2,4
2	Operating Life Test	1005	-40°C, V _{CC} = 6V, - 168 hrs - 500 hrs	1	30 30	0 0	2,3
			-40°C, V _{CC} = 4V, - 168 hrs - 500 hrs	1	31 31	0 0	2,4
3	Retention Bake	1005	150°C – 168 hrs – 500 hrs	1	60 60	0 0	3
4	Retention Bake	1005	250°C – 168 hrs – 500 hrs	1	60 60	0 0	2,3
5	Write/Erase Cycling		10,000 cycles 50,000 cycles 100,000 cycles	1	63 63 63	0 0 0	2,3
			10,000 cycles 50,000 cycles 100,000 cycles	1	63 63 63	0 0 0	2,4
5	Temperature, Humidity, Bias	CECC 90,000	85°C, RH = 85%, V _{CC} = 5.5V, – 168 hrs – 500 hrs	1	60 60	0 0	1,3
6	Temperature Cycling	1010C	–65 to 150°C, – 500 cycles – 1000 cycles	1	60 60	0 0	1,3
7	Pressure Pot		121°C, 2 Atm, RH = 100%, – 96 hrs – 168 hrs – 240 hrs	1	60 60 60	0 0 0	1,3

Table 5. SO44 Plastic Package - Die Related Tests, Catania M5 Diffusion Line

Note: 1. Samples previously submitted to preconditioning flow for Surface Mounting devices according to the Package Related tests (previous page).
2. Test performed on CDIP48 package.
3. Test performed on M29F400B device.
4. Test performed on M29W400B device.

57

If you have any questions or suggestion concerning the matters raised in this document please send them to the following electronic mail address:

ask.memory@st.com

(for general enquiries)

Please remember to include your name, company, location, telephone number and fax number.

Information furnished is believed to be accurate and reliable. However, STMicroelectronics assumes no responsibility for the consequences of use of such information nor for any infringement of patents or other rights of third parties which may result from its use. No license is granted by implication or otherwise under any patent or patent rights of STMicroelectronics. Specifications mentioned in this publication are subject to change without notice. This publication supersedes and replaces all information previously supplied. STMicroelectronics products are not authorized for use as critical components in life support devices or systems without express written approval of STMicroelectronics.

The ST logo is registered trademark of STMicroelectronics (B) 2000 STMicroelectronics - All Rights Reserved

All other names are the property of their respective owners.

STMicroelectronics GROUP OF COMPANIES Australia - Brazil - China - Finland - France - Germany - Hong Kong - India - Italy - Japan - Malaysia - Malta - Morocco -Singapore - Spain - Sweden - Switzerland - United Kingdom - U.S.A.

http://www.st.com

57