



TECHNICAL DATA SHEET

GTI-A-3000

Base material Polyolefin with hot melt adhesive

Color Black

Typical Properties

Physical	Value	Standard	Test Method
Shrink ratio	3:1		
Tensile strength	12 N/mm ² min.	-	IEC 60684-2-19
Elongation at break	350 % min.	-	IEC 60684-2-19
Longitudinal change	+0/ -10 %	-	IEC 60684-2-9
Concentricity	60 % min.	-	IEC 60684-2-3
Secant Modulus	85 N/mm ²	-	IEC 60684-2-37
Relative Density	1.15 g/cm ³	-	IEC 60684-2-4

Thermal	Value	Standard	Test Method
Continuous Operating Temperature	-55°C to +80°C	-	IEC 60684-2-37
Shrink Temperature	120°C min. 280 °C max.		
Heat Shock 200 °C / 4 hrs		-	IEC 60684-2-6
Tensile strength		-	IEC 60684-2-19
Elongation at break		-	IEC 60684-2-19
Heat Aging 150 °C / 168 hrs		-	IEC 60684-2-39
Elongation at break	350 % min.	-	IEC 60684-2-19
Low Temperature Flexibility	No cracking after bending	-	IEC 60684-2-14
Copper Corrosion	No corrosion	-	IEC 60684-2-33
Flammability	Not self extinguishing	-	IEC 60684-2-26

Electrical	Value	Standard	Test Method
Dielectric Strength	180 kV/cm	-	IEC 60684-2-21
Volume resistivity	1*10 ¹⁴ Ohm/cm	-	IEC 60684-2-23

Chemical	Value	Standard	Test Method
Chemical Resistance	Good	-	IEC 60684-2-36
Sealing	IP 68	IEC529	VDE 0278

Environmental	Value	Standard	Test Method
Halogen free	No	BS 6853	N/a
RoHS compliant	Yes	2002/95/EEC Incl. Exemption Oct. 13, 2005 EU 2005/717/EC	N/a
Decabromo diphenylether (PBDE) Free	No		N/a

Technical Information provided consists of typical product data and should not be used for specification purposes.
Unless otherwise specified in the test method, all tests are performed at room temperature.

Documentation

Important note to the purchaser.

All statements, technical information and recommendations contained herein are based on tests 3M believes to be reliable, but their accuracy and completeness are not guaranteed.

The user shall be responsible for determining the suitability of the products for his particular application.

To discuss your application requirements please contact your representative

Issue date 1/1/2006
Replacing 13/9/2005
Page 1 of 2



TECHNICAL DATA SHEET

GTI-A-3000

Product Guide - Table 1

Part Number	Expanded ID (min.)		Recovered ID (max.)		Total Recovered Wall Thickness (nominal)		Recovered Adhesive Wall Thickness (nominal)	
	mm.		mm.		mm.		mm.	
3.0	3.0		1.0		1.0		0.5	
9.0	9.0		3.0		1.4		0.6	
18.0	18.0		6.0		2.2		0.8	
39.0	39.0		13.0		2.5		1.0	

Storage Conditions

Temperature: min. -50 °C
max. +50 °C

Moisture: max. 75 %

Important note to the purchaser.

All statements, technical information and recommendations contained herein are based on tests 3M believes to be reliable, but their accuracy and completeness are not guaranteed.

The user shall be responsible for determining the suitability of the products for his particular application.

To discuss your application requirements please contact your representative